

AMENDMENTS TO THE SPECIFICATION

Please replace Table 2, on page 23 with the following amended Table 2:

Table 2

Various physical properties of barium titanate powder

	Loose bulk density	packed bulk density	Atomic ratio Ba/Ti	chlorine content
Example 1	g/cm ³	g/cm ³		ppm
Example 2 1	1.61	2.04	1.000	26
Example 3 2	1.55	2.00	1.001	35
Example [[4]] 3	1.44	2.00	0.998	46
Comparative Example 4	1.45	1.92	0.997	29
Comparative Example 1	1.40	1.78	0.998	-
Comparative Example 2	1.08	1.45	0.997	57
Comparative Example 3	1.07	1.45	0.997	-